

## POROUS CERAMIC/POROUS POLYMER LAYERED SCAFFOLDS FOR THE REPAIR AND REGENERATION OF TISSUE

### Field of the Invention

The present invention relates generally to the field of tissue repair, and more particularly to porous biocompatible ceramics, polymers and composites for use in tissue scaffolds.

### Background of the Invention

Porous ceramic materials such as hydroxyapatite, soluble glasses and ceramic foams have been used as scaffolds for the ingrowth of tissue due to compositional and morphological biocompatibility. For example, the porosity of such materials promotes cell infiltration. A variety of methods are used to prepare porous ceramic scaffolds (prostheses), such as hydrothermally treating animal bone or coral, burning off polymer beads mixed into a ceramic body, vapor deposition on foam, infiltration of polymer foam with a ceramic slip and foaming a ceramic slip.

One limitation exhibited by porous ceramic materials is their inherent brittleness. Attempts to address this limitation have included back-filling a ceramic foam with monomer solutions of PMMA or PLA, draining excess solution from the ceramic foam then polymerizing through curing and/or drying in order to impart some toughness to the ceramic foam. Others have proposed laminating solid or porous polymeric layers to a ceramic foam structure.

Independent from proposed uses in combination with ceramics, polymeric foams have utility in the repair and regeneration of tissue. For example, amorphous, polymeric foam has been used to fill voids in bone. Various methods have been explored for preparing the polymer foams, using, e.g., leachables; vacuum foaming techniques; precipitated polymer gel masses; and polymer melts with fugitive compounds that sublime at temperatures greater than room temperature. The formation of biocompatible absorbable foams by lyophilization are discussed in a copending patent application entitled "Porous Tissue Scaffoldings for the Repair and Regeneration of Tissue", assigned to

Ethicon, Inc., docket number 09/345096, filed June 30, 1999, hereby incorporated by reference.

Hinsch et al. (EP0274898) describes a porous open cell foam of polyhydroxy acids for the in-growth of blood vessels and cells. The foam can be reinforced with fibers, yarns, braids, knitted fabrics, scrims and the like.

Athanasίου et al. (U.S. Patent No. 5,607,474) have proposed using a two-layer polymeric foam device for repairing osteochondral defects at a location where two dissimilar types of tissue are present. The two polymeric layers are prepared separately, and joined together at a subsequent step. Each of the layers is designed to have stiffness and compressibility values that correspond respectively to cartilage and bone tissue, mimicking the cartilage/bone interface. However, the Athanasίου device exhibits an abrupt change in properties from one layer to the next, whereas the juncture of cartilage and bone displays a gradual transition, with cartilage cells gradually changing cell morphology and orientation depending on the location relative to the underlying bone structure. Further, collagen fiber orientation within the matrix also changes relative to its location in the structure.

H. Levene et al., U.S. Patent No. 6,103,255 describes a process used for making a scaffold having a substantially continuous polymer phase with a distribution of large and small pore sizes, with the small pores contained in the walls of the large pores.

In a study done by G. Niederauer et al. and reported in *Biomaterials* 21 (2000) 2561, scaffolds for articular cartilage repair were prepared from layers of polylactic/polyglycolic acid (PLG) and polylactic/polyglycolic acid reinforced with fibers of the same material, bioglass or calcium sulfate. The PLG layer was made porous in all cases by expanding a precipitated gel mass of polymer under vacuum at elevated temperatures. The reinforced layers were made porous in a similar fashion after incorporating the reinforcement in the polymer solution and prior to precipitation of the polymeric gel mass. Once the two layers were fabricated, they were adjoined using a small amount of solvent to glue the two layers together.

The use of a porous polymer for the purpose of engineering cartilage is described in the patent by T. Mahood et al. (EP1027897A1) which discloses a multi-layer polymer scaffold in which the layers are attached by

successive dip coating or by the attachment of the two layers to a third. The third layer is described as a barrier to cell diffusion, thus confining chondrocytes to the polymer layer and osteoblasts to the ceramic layer.

5 Kreklau et al. in *Biomaterials* 20 (1999) 1743 have evaluated a fibrous polymeric fleece attached to a porous ceramic material, for the purpose of culturing chondrocytes in the polymeric scaffold while simultaneously providing a bone formation inducing absorbable material to simulate articular cartilage. In this study, a fibrin-cell-solution was used to affix the ceramic and polymeric layers by way of encapsulation with the intent that the phases would  
10 interact *in vitro* in order to create a mechanically stressable junction. The authors discuss the possibility of providing the surfaces of the layers with teeth to increase shear strength. However, there is no mechanism by which the two different layers are interlocked to resist delaminating forces in directions perpendicular to the laminate function and there is an abrupt transition between the two layers.  
15

It would be advantageous to overcome the above mentioned limitations of known scaffolds.

#### Summary of Invention

20 The limitations of the prior art are overcome by the present invention which includes a composite scaffold with a ceramic phase having a first plurality of pores and a polymer phase having a second plurality of pores. The polymer phase is attached to the ceramic phase at an interphase region with the polymer phase infused at least partially into the first plurality of pores in the interphase region. In accordance with a method for making the scaffold, the  
25 ceramic phase is placed in contact with a polymer solution which infuses into the pores of the ceramic phase. The polymer solution is then foamed to produce a polymer foam interlocked with the ceramic phase.

#### Brief Description of Figures

30 Figure 1 is a perspective view of a composite scaffold in accordance with a first embodiment of the present invention;

Figure 2 is a cross-sectional view of the scaffold of Figure 1 taken along section line II-II and looking in the direction of the arrows;

Figure 3 is a perspective view of a scaffold in accordance with a second exemplary embodiment of the present invention;

Figure 4 is a cross-sectional view of the scaffold of Figure 3 taken along section line IV-IV and looking in the direction of the arrows;

Figure 5 is a perspective, partially phantom view of a scaffold in accordance with a third exemplary embodiment of the present invention;

Figure 6 is a perspective view of a truss structure incorporated in the scaffold of Figure 5;

Figure 7 is an enlarged view of a segment VII of the truss structure of Figure 6;

Figure 8 is a perspective view of an alternative truss structure that may be incorporated in a scaffold in accordance with the present invention; and

Figure 9 is a scanning electron micrograph of the cross-section of the porous ceramic/porous polymer interphase region of a scaffold in accordance with the present invention, such as shown in Figure 1.

#### Detailed Description of the Invention

The present invention relates to bi- or multi-layered scaffolds with a porous, bioabsorbable polymer layer attached to a porous ceramic layer via a porous transitional interface. The scaffolds are particularly useful in the repair/regeneration of defects present at a junction of tissue types exhibiting a transitional or gradient morphology/physiology such as at the cartilage/bone junction. The present invention can be utilized to repair/regenerate a tissue junction by inducing one cell type to proliferate in the polymer phase of the scaffold and a second cell type to grow in the ceramic phase of the scaffold. Examples of such junction regeneration sites are (a) spinal disc (nuclear and annular cells cultured on the polymer phase and osteoblasts cultured in the ceramic phase); (b) articular or meniscal cartilage (chondrocytes, or fibrochondrocytes, respectively, cultured on the polymer phase and osteoblasts cultured in the ceramic). The present invention may also be utilized to repair the meniscus, fibrocartilage, tendons, and ligaments. The features of the porous

polymer phase can be controlled to suit a desired application by choosing the appropriate conditions during the process of lyophilization, or freeze drying. The porous polymer foam can be directly lyophilized into the ceramic structure creating a multiphasic material composed of a polymer foam with or without reinforcement structures, an interphase zone of polymer foam diffused and expanded within the porous ceramic, and a porous ceramic. These features in partially or completely absorbable implants have advantages over the prior art where the scaffolds are typically isotropic or random structures.

One of the major weaknesses of the prior art regarding laminated scaffolds is that the layers are not completely integrated and are subject to delamination under *in vivo* conditions. The present invention solves the problem of delamination by the lyophilization of a porous polymer foam in the presence of a porous ceramic, interlocking the porous polymeric foam with the porous ceramic by way of an interphase zone of porous polymer infiltrated into the porous ceramic. This interphase zone exhibits a microporous polymer foam located within the macropores of a porous ceramic. The interpenetration of the two porous layers creates a strong mechanical junction while simultaneously providing a gradual change in material properties for the purpose of regenerating different tissues or co-culturing different types of cells in intimate contact with one another. The interconnecting pores and channels facilitate the transport of nutrients and/or invasion of cells into the scaffold, facilitating the ingrowth of tissue. This transitional composite structure more closely mimics naturally occurring tissue junctions. The present invention therefore facilitates cellular organization and the regeneration of tissue junctions with normal morphology and physiology.

The features of a scaffold in accordance with the present invention can be tailored to suit a particular application by selecting the appropriate ceramic, polymer and conditions for lyophilization of the polymer to obtain one or more of the following properties: (1) interconnecting polymer foams attached to the porous ceramic (2) a variety of porosities ranging from about 20% to about 98% for the polymer foam; (3) a gradient in the pore size between the polymer and ceramic; (4) channels that run through the porous polymer foam for improved cell invasion, vascularization and nutrient diffusion; and (5) micro-

patterning of pores or the addition of other polymer structures on the surface of the polymer for cellular organization or to limit cellular invasion.

In addition, the scaffold can include (1) porous composites with a composition gradient to elicit or take advantage of different cell response to different materials; (2) reinforcement with knitted, braided, woven, or non-woven fabrics or meshes, or truss structures in order to impart desired mechanical properties; (3) blends of different polymer compositions to create a polymer phase that has portions that will break down at different rates; (4) multi-layer composite structures with layers of alternating porous ceramics and polymers; (5) a polymer phase co-lyophilized or coated with pharmaceutically active compounds; (6) a ceramic phase coated with pharmaceutically active compounds such as growth factors; and/or (7) cells which may be cultured prior to or at the time of implantation.

Figures 1 and 2 show a composite scaffold 10 with a porous polymer phase 12 and porous ceramic phase 14, which are mechanically interlocked at interphase region 16. In the interphase region 16 shown in the sectional view of Figure 2, macropores 15 in ceramic phase 14 are filled with polymer phase 12. Polymer phase 12, in turn contains micropores 18.

The infusion of the polymer phase 12 into the ceramic phase 14 securely fastens the two phases 12, 14 and supports the brittle structure of the porous ceramic phase 14. The polymer phase 12 acts as a cushion to dissipate impact energy to shield the brittle ceramic phase 14 from catastrophically damaging stresses. In addition, the communicating pores 15, 18 encourage the growth of different types of cells, promoting the regeneration of different adjoining layers of tissue at an injured tissue junction.

The macropores 15 in the ceramic phase 14 are interconnected, and may be selected to have pore sizes ranging from 25 to 600 microns, preferably from 100 to 250 microns. The micropores 18 in the polymer phase 12 are also interconnected and range in size from about 10 to 250 microns, preferably 30 to 150 microns. The terms "micropore" and "macropore" are used to designate the two size scales of pores found in the scaffold 10. If the brittle ceramic phase 14 is cracked, the polymer phase 12 in the interphase region 16 holds the scaffold together. The composite scaffold 10 facilitates the creation of

a strong bond between different types of tissue such as in the repair and regeneration of articular cartilage, meniscus, and spinal discs.

5 The scaffold 10 may be made by infiltrating the porous ceramic phase 14 with the desired elastomeric polymer phase 12, and then causing the polymer phase 12 to foam. The polymer phase 12 may be foamed by lyophilization, supercritical solvent foaming (i.e., as described in EP 464163B1), gas injection extrusion, gas injection molding or casting with an extractable material, e.g., salts, sugar or by any other means known to those skilled in the art. Currently, it is preferred to foam the polymer 12 by lyophilization (freeze drying). Suitable methods for lyophilizing elastomeric polymers to form foams are described in pending patent applications entitled, "Process for Manufacturing Biomedical Foams" assigned to Ethicon, Inc., docket number 09/345095, filed 10 June 30, 1999 and "Porous Tissue Scaffoldings for the Repair or Regeneration of Tissue" assigned to Ethicon, Inc., docket number 09/345096, filed June 30, 1999, hereby incorporated herein by reference.

15 The first step in making the scaffold 10 is to dissolve the desired elastomeric polymer to form phase 12 in a solvent, forming a polymer solution. The polymer solution is brought into contact with the porous ceramic phase 14 and the low viscosity polymeric solution wicks via capillary action into the pores of the ceramic layer 14. Other infiltrating methods include injecting the solution into the ceramic layer 14 under pressure and vacuum assisted infiltration.

20 In the wicking method, the ceramic phase 14 is only partially submerged in polymer solution, which is contained in a receptacle or mold. The mold may be made from any material that does not interfere with the polymer-solvent system and is preferably formed from a heat conductive material. The preferred method of partially submerging the ceramic phase 14 is to place shims (spacers) on the inside bottom of the mold, and place the ceramic layer on the shims. The thickness of the spacers and the volume of polymer charged in the mold controls the thickness of the polymer phase 12 and the interphase region 16.

25 The above-described mold assembly is then placed in a freeze dryer and subject to directional cooling (through the wall of the mold that is in contact with the freeze dryer shelf) in a thermal cycle. The heat transfer front moves upwards from the lyophilizer shelf through the mold and into the polymer





polyoxaesters, polyamidoesters, polyoxaesters containing amine groups, poly(anhydrides), polyphosphazenes, biomolecules and blends thereof.

For the purpose of this invention aliphatic polyesters include but are not limited to homopolymers and copolymers of lactide (which includes lactic acid, D-,L- and meso lactide), glycolide (including glycolic acid),  $\epsilon$ -caprolactone, p-dioxanone (1,4-dioxan-2-one), trimethylene carbonate (1,3-dioxan-2-one), alkyl derivatives of trimethylene carbonate,  $\delta$ -valerolactone,  $\beta$ -butyrolactone,  $\gamma$ -butyrolactone,  $\epsilon$ -decalactone, hydroxybutyrate, hydroxyvalerate, 1,4-dioxepan-2-one (including its dimer 1,5,8,12-tetraoxacyclotetradecane-7,14-dione), 1,5-dioxepan-2-one, 6,6-dimethyl-1,4-dioxan-2-one, 2,5-diketomorpholine, pivalolactone, alpha, alpha-diethylpropiolactone, ethylene carbonate, ethylene oxalate, 3-methyl-1,4-dioxane-2,5-dione, 3,3-diethyl-1,4-dioxan-2,5-dione, 6,8-dioxabicyclooctane-7-one and polymer blends thereof.

Poly(iminocarbonates) for the purpose of this invention include those described by Kemnitzer and Kohn, in the Handbook of Biodegradable Polymers, edited by Domb, Kost and Wisemen, Hardwood Academic Press, 1997, pages 251-272. Copoly(ether-esters) for the purpose of this invention include those copolyester-ethers described by Cohn and Younes *J. Biomater. Res.*, **22**, (1988) 993, and Cohn, *Polymer Preprints*, **30**(1), (1989) 498.

Polyalkylene oxalates for the purpose of this invention include those described in U.S. Patent Nos. 4,208,511; 4,141,087; 4,130,639; 4,140,678; 4,105,034; and 4,205,399 (incorporated by reference herein).

Polyphosphazenes for the purpose of this invention include co-, ter- and higher order mixed monomer based polymers made from L-lactide, D,L-lactide, lactic acid, glycolide, glycolic acid, para-dioxanone, trimethylene carbonate and  $\epsilon$ -caprolactone those described by Allcock in The Encyclopedia of Polymer Science, Wiley Intersciences, John Wiley & Sons, **13** (1988) 31, and by Vandorpe, Schacht, Dejardin and Lemmouchi in the Handbook of Biodegradable Polymers, edited by Domb, Kost and Wisemen, Hardwood Academic Press, (1997) 161 (which are hereby incorporated by reference herein).

Polyanhydrides for the purpose of this invention include those from diacids of the form  $\text{HOOC-C}_6\text{H}_4\text{-O-(CH}_2\text{)}_m\text{-O-C}_6\text{H}_4\text{-COOH}$  where m is an integer

in the range of from 2 to 8 and copolymers thereof with aliphatic alpha-omega diacids of up to 12 carbons.

Polyoxaesters, polyoxaamides and polyoxaesters containing amines and/or amino groups for the purpose of this invention include those described in one or more of the following U.S. Patent Nos. 5,464,929; 5,595,751; 5,597,579; 5,607,687; 5,618,552; 5,620,698; 5,645,850; 5,648,088; 5,698,213; 5,700,583; and 5,859,150 (which are incorporated herein by reference). Polyorthoesters for the purpose of this invention include those described by Heller in the Handbook of Biodegradable Polymers, edited by Domb, Kost and Wisemen, Hardwood Academic Press, (1997), 99 (hereby incorporated herein by reference).

Aliphatic polyesters are preferred for making the polymers phase 12 of the scaffold 10. Aliphatic polyesters can be homopolymers, copolymers (random, block, segmented, tapered blocks, graft, triblock, etc.) having a linear, branched or star structure. The preferred morphology of the copolymer chains is linear. Suitable monomers for making aliphatic homopolymers and copolymers may be selected from the group consisting of, but not limited to, lactic acid, lactide (including L-, D-, meso and D,L mixtures), glycolic acid, glycolide,  $\epsilon$ -caprolactone, p-dioxanone (1,4-dioxan-2-one), trimethylene carbonate (1,3-dioxan-2-one), delta-valerolactone, beta-butyrolactone, epsilon-decalactone, 2,5-diketomorpholine, pivalolactone, alpha, alpha-diethylpropiolactone, ethylene carbonate, ethylene oxalate, 3-methyl-1,4-dioxane-2,5-dione, 3,3-diethyl-1,4-dioxan-2,5-dione, gamma-butyrolactone, 1,4-dioxepan-2-one, 1,5-dioxepan-2-one, 6,6-dimethyl-dioxepan-2-one, 6,8-dioxabicyclooctane-7-one and combinations thereof.

Elastomeric copolymers also are particularly useful in the present invention. Suitable bioabsorbable, biocompatible elastomers include, but are not limited to, those selected from the group consisting of elastomeric copolymers of  $\epsilon$ -caprolactone and glycolide (preferably having a mole ratio of  $\epsilon$ -caprolactone to glycolide of from about 35:65 to about 65:35, more preferably from 45:55 to 35:65); elastomeric copolymers of  $\epsilon$ -caprolactone and lactide, including L-lactide, D-lactide blends thereof or lactic acid copolymers (preferably having a mole ratio of  $\epsilon$ -caprolactone to lactide of from about 35:65 to about 65:35 and more

preferably from 45:55 to 30:70 or from about 95:5 to about 85:15); elastomeric copolymers of p-dioxanone (1,4-dioxan-2-one) and lactide including L-lactide, D-lactide and lactic acid (preferably having a mole ratio of p-dioxanone to lactide of from about 40:60 to about 60:40); elastomeric copolymers of  $\epsilon$ -caprolactone and p-dioxanone (preferably having a mole ratio of  $\epsilon$ -caprolactone to p-dioxanone of from about from 30:70 to about 70:30); elastomeric copolymers of p-dioxanone and trimethylene carbonate (preferably having a mole ratio of p-dioxanone to trimethylene carbonate of from about 30:70 to about 70:30); elastomeric copolymers of trimethylene carbonate and glycolide (preferably having a mole ratio of trimethylene carbonate to glycolide of from about 30:70 to about 70:30); elastomeric copolymer of trimethylene carbonate and lactide including L-lactide, D-lactide, blends thereof or lactic acid copolymers (preferably having a mole ratio of trimethylene carbonate to lactide of from about 30:70 to about 70:30); and blends thereof. Examples of suitable bioabsorbable elastomers are also described in U.S. Patent Nos. 4,045,418, 4,057,537 and 5,468,253, all hereby incorporated by reference.

In the preferred embodiments of this invention, the elastomer from which the foams are formed will exhibit a percent elongation greater than about 200 percent and preferably greater than about 500 percent. The properties that determine the degree of elasticity of the bioabsorbable elastomer are achieved while maintaining a tensile strength greater than about 500 psi, preferably greater than about 1,000 psi, and a tear strength of greater than about 50 lbs/inch, preferably greater than about 80 lbs/inch.

The polymers or copolymer suitable for forming the polymers phase 12 of the implant 10 for any particular application depends on several factors. The chemical composition, spatial distribution of the constituents, the molecular weight of the polymers and the degree of crystallinity, all dictate to some extent the *in vitro* and *in vivo* behavior of the polymer. However, the selection of the polymer to make gradient foams for tissue regeneration largely depends on (but is not limited to) the following factors: (a) bioabsorption (or biodegradation) kinetics; (b) *in vivo* mechanical performance; (c) cell response to the material in terms of cell attachment, proliferation, migration and differentiation and (d) biocompatibility.

5 The ability of the polymer phase to resorb in a timely fashion *in vivo* is critical. The differences in the absorption time under *in vivo* conditions can also be the basis for combining two different copolymers. For example, a copolymer of 35:65  $\epsilon$ -caprolactone and glycolide (a relatively fast absorbing polymer) is blended with 40:60  $\epsilon$ -caprolactone and (L)lactide copolymer (a relatively slow absorbing polymer) to form a foam. Such a foam could be processed to yield several different physical structures depending upon the technique used. The two constituents can be either randomly inter-connected bicontinuous phases, or have a gradient or laminate composition with an integrated interface between the constituent layers. The microstructure of these foams can be optimized to regenerate or repair the desired anatomical features of the tissue that is being engineered.

10  
15  
20  
25  
30  
35  
40  
45  
50  
55  
60  
65  
70  
75  
80  
85  
90  
95  
100  
105  
110  
115  
120  
125  
130  
135  
140  
145  
150  
155  
160  
165  
170  
175  
180  
185  
190  
195  
200  
205  
210  
215  
220  
225  
230  
235  
240  
245  
250  
255  
260  
265  
270  
275  
280  
285  
290  
295  
300  
305  
310  
315  
320  
325  
330  
335  
340  
345  
350  
355  
360  
365  
370  
375  
380  
385  
390  
395  
400  
405  
410  
415  
420  
425  
430  
435  
440  
445  
450  
455  
460  
465  
470  
475  
480  
485  
490  
495  
500  
505  
510  
515  
520  
525  
530  
535  
540  
545  
550  
555  
560  
565  
570  
575  
580  
585  
590  
595  
600  
605  
610  
615  
620  
625  
630  
635  
640  
645  
650  
655  
660  
665  
670  
675  
680  
685  
690  
695  
700  
705  
710  
715  
720  
725  
730  
735  
740  
745  
750  
755  
760  
765  
770  
775  
780  
785  
790  
795  
800  
805  
810  
815  
820  
825  
830  
835  
840  
845  
850  
855  
860  
865  
870  
875  
880  
885  
890  
895  
900  
905  
910  
915  
920  
925  
930  
935  
940  
945  
950  
955  
960  
965  
970  
975  
980  
985  
990  
995  
1000  
1005  
1010  
1015  
1020  
1025  
1030  
1035  
1040  
1045  
1050  
1055  
1060  
1065  
1070  
1075  
1080  
1085  
1090  
1095  
1100  
1105  
1110  
1115  
1120  
1125  
1130  
1135  
1140  
1145  
1150  
1155  
1160  
1165  
1170  
1175  
1180  
1185  
1190  
1195  
1200  
1205  
1210  
1215  
1220  
1225  
1230  
1235  
1240  
1245  
1250  
1255  
1260  
1265  
1270  
1275  
1280  
1285  
1290  
1295  
1300  
1305  
1310  
1315  
1320  
1325  
1330  
1335  
1340  
1345  
1350  
1355  
1360  
1365  
1370  
1375  
1380  
1385  
1390  
1395  
1400  
1405  
1410  
1415  
1420  
1425  
1430  
1435  
1440  
1445  
1450  
1455  
1460  
1465  
1470  
1475  
1480  
1485  
1490  
1495  
1500  
1505  
1510  
1515  
1520  
1525  
1530  
1535  
1540  
1545  
1550  
1555  
1560  
1565  
1570  
1575  
1580  
1585  
1590  
1595  
1600  
1605  
1610  
1615  
1620  
1625  
1630  
1635  
1640  
1645  
1650  
1655  
1660  
1665  
1670  
1675  
1680  
1685  
1690  
1695  
1700  
1705  
1710  
1715  
1720  
1725  
1730  
1735  
1740  
1745  
1750  
1755  
1760  
1765  
1770  
1775  
1780  
1785  
1790  
1795  
1800  
1805  
1810  
1815  
1820  
1825  
1830  
1835  
1840  
1845  
1850  
1855  
1860  
1865  
1870  
1875  
1880  
1885  
1890  
1895  
1900  
1905  
1910  
1915  
1920  
1925  
1930  
1935  
1940  
1945  
1950  
1955  
1960  
1965  
1970  
1975  
1980  
1985  
1990  
1995  
2000  
2005  
2010  
2015  
2020  
2025  
2030  
2035  
2040  
2045  
2050  
2055  
2060  
2065  
2070  
2075  
2080  
2085  
2090  
2095  
2100  
2105  
2110  
2115  
2120  
2125  
2130  
2135  
2140  
2145  
2150  
2155  
2160  
2165  
2170  
2175  
2180  
2185  
2190  
2195  
2200  
2205  
2210  
2215  
2220  
2225  
2230  
2235  
2240  
2245  
2250  
2255  
2260  
2265  
2270  
2275  
2280  
2285  
2290  
2295  
2300  
2305  
2310  
2315  
2320  
2325  
2330  
2335  
2340  
2345  
2350  
2355  
2360  
2365  
2370  
2375  
2380  
2385  
2390  
2395  
2400  
2405  
2410  
2415  
2420  
2425  
2430  
2435  
2440  
2445  
2450  
2455  
2460  
2465  
2470  
2475  
2480  
2485  
2490  
2495  
2500  
2505  
2510  
2515  
2520  
2525  
2530  
2535  
2540  
2545  
2550  
2555  
2560  
2565  
2570  
2575  
2580  
2585  
2590  
2595  
2600  
2605  
2610  
2615  
2620  
2625  
2630  
2635  
2640  
2645  
2650  
2655  
2660  
2665  
2670  
2675  
2680  
2685  
2690  
2695  
2700  
2705  
2710  
2715  
2720  
2725  
2730  
2735  
2740  
2745  
2750  
2755  
2760  
2765  
2770  
2775  
2780  
2785  
2790  
2795  
2800  
2805  
2810  
2815  
2820  
2825  
2830  
2835  
2840  
2845  
2850  
2855  
2860  
2865  
2870  
2875  
2880  
2885  
2890  
2895  
2900  
2905  
2910  
2915  
2920  
2925  
2930  
2935  
2940  
2945  
2950  
2955  
2960  
2965  
2970  
2975  
2980  
2985  
2990  
2995  
3000  
3005  
3010  
3015  
3020  
3025  
3030  
3035  
3040  
3045  
3050  
3055  
3060  
3065  
3070  
3075  
3080  
3085  
3090  
3095  
3100  
3105  
3110  
3115  
3120  
3125  
3130  
3135  
3140  
3145  
3150  
3155  
3160  
3165  
3170  
3175  
3180  
3185  
3190  
3195  
3200  
3205  
3210  
3215  
3220  
3225  
3230  
3235  
3240  
3245  
3250  
3255  
3260  
3265  
3270  
3275  
3280  
3285  
3290  
3295  
3300  
3305  
3310  
3315  
3320  
3325  
3330  
3335  
3340  
3345  
3350  
3355  
3360  
3365  
3370  
3375  
3380  
3385  
3390  
3395  
3400  
3405  
3410  
3415  
3420  
3425  
3430  
3435  
3440  
3445  
3450  
3455  
3460  
3465  
3470  
3475  
3480  
3485  
3490  
3495  
3500  
3505  
3510  
3515  
3520  
3525  
3530  
3535  
3540  
3545  
3550  
3555  
3560  
3565  
3570  
3575  
3580  
3585  
3590  
3595  
3600  
3605  
3610  
3615  
3620  
3625  
3630  
3635  
3640  
3645  
3650  
3655  
3660  
3665  
3670  
3675  
3680  
3685  
3690  
3695  
3700  
3705  
3710  
3715  
3720  
3725  
3730  
3735  
3740  
3745  
3750  
3755  
3760  
3765  
3770  
3775  
3780  
3785  
3790  
3795  
3800  
3805  
3810  
3815  
3820  
3825  
3830  
3835  
3840  
3845  
3850  
3855  
3860  
3865  
3870  
3875  
3880  
3885  
3890  
3895  
3900  
3905  
3910  
3915  
3920  
3925  
3930  
3935  
3940  
3945  
3950  
3955  
3960  
3965  
3970  
3975  
3980  
3985  
3990  
3995  
4000  
4005  
4010  
4015  
4020  
4025  
4030  
4035  
4040  
4045  
4050  
4055  
4060  
4065  
4070  
4075  
4080  
4085  
4090  
4095  
4100  
4105  
4110  
4115  
4120  
4125  
4130  
4135  
4140  
4145  
4150  
4155  
4160  
4165  
4170  
4175  
4180  
4185  
4190  
4195  
4200  
4205  
4210  
4215  
4220  
4225  
4230  
4235  
4240  
4245  
4250  
4255  
4260  
4265  
4270  
4275  
4280  
4285  
4290  
4295  
4300  
4305  
4310  
4315  
4320  
4325  
4330  
4335  
4340  
4345  
4350  
4355  
4360  
4365  
4370  
4375  
4380  
4385  
4390  
4395  
4400  
4405  
4410  
4415  
4420  
4425  
4430  
4435  
4440  
4445  
4450  
4455  
4460  
4465  
4470  
4475  
4480  
4485  
4490  
4495  
4500  
4505  
4510  
4515  
4520  
4525  
4530  
4535  
4540  
4545  
4550  
4555  
4560  
4565  
4570  
4575  
4580  
4585  
4590  
4595  
4600  
4605  
4610  
4615  
4620  
4625  
4630  
4635  
4640  
4645  
4650  
4655  
4660  
4665  
4670  
4675  
4680  
4685  
4690  
4695  
4700  
4705  
4710  
4715  
4720  
4725  
4730  
4735  
4740  
4745  
4750  
4755  
4760  
4765  
4770  
4775  
4780  
4785  
4790  
4795  
4800  
4805  
4810  
4815  
4820  
4825  
4830  
4835  
4840  
4845  
4850  
4855  
4860  
4865  
4870  
4875  
4880  
4885  
4890  
4895  
4900  
4905  
4910  
4915  
4920  
4925  
4930  
4935  
4940  
4945  
4950  
4955  
4960  
4965  
4970  
4975  
4980  
4985  
4990  
4995  
5000  
5005  
5010  
5015  
5020  
5025  
5030  
5035  
5040  
5045  
5050  
5055  
5060  
5065  
5070  
5075  
5080  
5085  
5090  
5095  
5100  
5105  
5110  
5115  
5120  
5125  
5130  
5135  
5140  
5145  
5150  
5155  
5160  
5165  
5170  
5175  
5180  
5185  
5190  
5195  
5200  
5205  
5210  
5215  
5220  
5225  
5230  
5235  
5240  
5245  
5250  
5255  
5260  
5265  
5270  
5275  
5280  
5285  
5290  
5295  
5300  
5305  
5310  
5315  
5320  
5325  
5330  
5335  
5340  
5345  
5350  
5355  
5360  
5365  
5370  
5375  
5380  
5385  
5390  
5395  
5400  
5405  
5410  
5415  
5420  
5425  
5430  
5435  
5440  
5445  
5450  
5455  
5460  
5465  
5470  
5475  
5480  
5485  
5490  
5495  
5500  
5505  
5510  
5515  
5520  
5525  
5530  
5535  
5540  
5545  
5550  
5555  
5560  
5565  
5570  
5575  
5580  
5585  
5590  
5595  
5600  
5605  
5610  
5615  
5620  
5625  
5630  
5635  
5640  
5645  
5650  
5655  
5660  
5665  
5670  
5675  
5680  
5685  
5690  
5695  
5700  
5705  
5710  
5715  
5720  
5725  
5730  
5735  
5740  
5745  
5750  
5755  
5760  
5765  
5770  
5775  
5780  
5785  
5790  
5795  
5800  
5805  
5810  
5815  
5820  
5825  
5830  
5835  
5840  
5845  
5850  
5855  
5860  
5865  
5870  
5875  
5880  
5885  
5890  
5895  
5900  
5905  
5910  
5915  
5920  
5925  
5930  
5935  
5940  
5945  
5950  
5955  
5960  
5965  
5970  
5975  
5980  
5985  
5990  
5995  
6000  
6005  
6010  
6015  
6020  
6025  
6030  
6035  
6040  
6045  
6050  
6055  
6060  
6065  
6070  
6075  
6080  
6085  
6090  
6095  
6100  
6105  
6110  
6115  
6120  
6125  
6130  
6135  
6140  
6145  
6150  
6155  
6160  
6165  
6170  
6175  
6180  
6185  
6190  
6195  
6200  
6205  
6210  
6215  
6220  
6225  
6230  
6235  
6240  
6245  
6250  
6255  
6260  
6265  
6270  
6275  
6280  
6285  
6290  
6295  
6300  
6305  
6310  
6315  
6320  
6325  
6330  
6335  
6340  
6345  
6350  
6355  
6360  
6365  
6370  
6375  
6380  
6385  
6390  
6395  
6400  
6405  
6410  
6415  
6420  
6425  
6430  
6435  
6440  
6445  
6450  
6455  
6460  
6465  
6470  
6475  
6480  
6485  
6490  
6495  
6500  
6505  
6510  
6515  
6520  
6525  
6530  
6535  
6540  
6545  
6550  
6555  
6560  
6565  
6570  
6575  
6580  
6585  
6590  
6595  
6600  
6605  
6610  
6615  
6620  
6625  
6630  
6635  
6640  
6645  
6650  
6655  
6660  
6665  
6670  
6675  
6680  
6685  
6690  
6695  
6700  
6705  
6710  
6715  
6720  
6725  
6730  
6735  
6740  
6745  
6750  
6755  
6760  
6765  
6770  
6775  
6780  
6785  
6790  
6795  
6800  
6805  
6810  
6815  
6820  
6825  
6830  
6835  
6840  
6845  
6850  
6855  
6860  
6865  
6870  
6875  
6880  
6885  
6890  
6895  
6900  
6905  
6910  
6915  
6920  
6925  
6930  
6935  
6940  
6945  
6950  
6955  
6960  
6965  
6970  
6975  
6980  
6985  
6990  
6995  
7000  
7005  
7010  
7015  
7020  
7025  
7030  
7035  
7040  
7045  
7050  
7055  
7060  
7065  
7070  
7075  
7080  
7085  
7090  
7095  
7100  
7105  
7110  
7115  
7120  
7125  
7130  
7135  
7140  
7145  
7150  
7155  
7160  
7165  
7170  
7175  
7180  
7185  
7190  
7195  
7200  
7205  
7210  
7215  
7220  
7225  
7230  
7235  
7240  
7245  
7250  
7255  
7260  
7265  
7270  
7275  
7280  
7285  
7290  
7295  
7300  
7305  
7310  
7315  
7320  
7325  
7330  
7335  
7340  
7345  
7350  
7355  
7360  
7365  
7370  
7375  
7380  
7385  
7390  
7395  
7400  
7405  
7410  
7415  
7420  
7425  
7430  
7435  
7440  
7445  
7450  
7455  
7460  
7465  
7470  
7475  
7480  
7485  
7490  
7495  
7500  
7505  
7510  
7515  
7520  
7525  
7530  
7535  
7540  
7545  
7550  
7555  
7560  
7565  
7570  
7575  
7580  
7585  
7590  
7595  
7600  
7605  
7610  
7615  
7620  
7625  
7630  
7635  
7640  
7645  
7650  
7655  
7660  
7665  
7670  
7675  
7680  
7685  
7690  
7695  
7700  
7705  
7710  
7715  
7720  
7725  
7730  
7735  
7740  
7745  
7750  
7755  
7760  
7765  
7770  
7775  
7780  
7785  
7790  
7795  
7800  
7805  
7810  
7815  
7820  
7825  
7830  
7835  
7840  
7845  
7850  
7855  
7860  
7865  
7870  
7875  
7880  
7885  
7890  
7895  
7900  
7905  
7910  
7915  
7920  
7925  
7930  
7935  
7940  
7945  
7950  
7955  
7960  
7965  
7970  
7975  
7980  
7985  
7990  
7995  
8000  
8005  
8010  
8015  
8020  
8025  
8030  
8035  
8040  
8045  
8050  
8055  
8060  
8065  
8070  
8075  
8080  
8085  
8090  
8095  
8100  
8105  
8110  
8115  
8120  
8125  
8130  
8135  
8140  
8145  
8150  
8155  
8160  
8165  
8170  
8175  
8180  
8185  
8190  
8195  
8200  
8205  
8210  
8215  
8220  
8225  
8230  
8235  
8240  
8245  
8250  
8255  
8260  
8265  
8270  
8275  
8280  
8285  
8290  
8295  
8300  
8305  
8310  
8315  
8320  
8325  
8330  
8335  
8340  
8345  
8350  
8355  
8360  
8365  
8370  
8375  
8380  
8385  
8390  
8395  
8400  
8405  
8410  
8415  
8420  
8425  
8430  
8435  
8440  
8445  
8450  
8455  
8460  
8465  
8470  
8475  
8480  
8485  
8490  
8495  
8500  
8505  
8510  
8515  
8520  
8525  
8530  
8535  
8540  
8545  
8550  
8555  
8560  
8565  
8570  
8575  
8580  
8585  
8590  
8595  
8600  
8605  
8610  
8615  
8620  
8625  
8630  
8635  
8640  
8645  
8650  
8655  
8660  
8665  
8670  
8675  
8680  
8685  
8690  
8695  
8700  
8705  
8710  
8715  
8720  
8725  
8730  
8735  
8740  
8745  
8750  
8755  
8760  
8765  
8770  
8775  
8780  
8785  
8790  
8795  
8800  
8805  
8810  
8815  
8820  
8825  
8830  
8835  
8840  
8845  
8850  
8855  
8860  
8865  
8870  
8875  
8880  
8885  
8890  
8895  
8900  
8905  
8910  
8915  
8920  
8925  
8930  
8935  
8940  
8945  
8950  
8955  
8960  
8965  
8970  
8975  
8980  
8985  
8990  
8995  
9000  
9005  
9010  
9015  
9020  
9025  
9030  
9035  
9040  
9045  
9050  
9055  
9060  
9065  
9070  
9075  
9080  
9085  
9090  
9095  
9100  
9105  
9110  
9115  
9120  
9125  
9130  
9135  
9140  
9145  
9150  
9155  
9160  
9165  
9170  
9175  
9180  
9185  
9190  
9195  
9200  
9205  
9210  
9215  
9220  
9225  
9230  
9235  
9240  
9245  
9250  
9255  
9260  
9265  
9270  
9275  
9280  
9285  
9290  
9295  
9300  
9305  
9310  
9315  
9320  
9325  
9330  
9335  
9340  
9345  
9350  
9355  
9360  
9365  
9370  
9375  
9380  
9385  
9390  
9395  
9400  
9405  
9410  
9415  
9420  
9425  
9430  
9435  
9440  
9445  
9450  
9455  
9460  
9465  
9470  
9475  
9480  
9485  
9490  
9495  
9500  
9505  
9510  
9515  
9520  
9525  
9530  
9535  
9540  
9545  
9550  
9555  
9560  
9565  
9570  
9575  
9580  
9585  
9590  
9595  
9600  
9605  
9610  
9615  
9620  
9625  
9630  
9635  
9640  
9645  
9650  
9655  
9660  
9665  
9670  
9675  
9680  
9685  
9690  
9695  
9700  
9705  
9710  
9715  
9720  
9725  
9730  
9735  
9740  
9745  
9750  
9755  
9760  
9765  
9770  
9775  
9780  
9785  
9790  
9795  
9800  
9805  
9810  
9815  
9820  
9825  
9830  
9835  
9840  
9845  
9850  
9855  
9860  
9865  
9870  
9875  
9880  
9885  
9890  
9895  
9900  
9905  
9910  
9915  
9920  
9925  
9930  
9935  
9940  
9945  
9950  
9955  
9960  
9965  
9970  
9975  
9980  
9985  
9990  
9995  
10000  
10005  
10010  
10015  
10020  
10025  
10030  
10035  
10040  
10045  
10050  
10055  
10060  
10065  
10070  
10075  
10080  
10085  
10090  
10095  
10100  
10105  
10110  
10115  
10120  
10125  
10130  
10135  
10140  
10145  
10150  
10155  
10160  
10165  
10170  
10175  
10180  
10185  
10190  
10195  
10200  
10205  
10210  
10215  
10220  
10225  
10230  
10235  
10240  
1

means of groove 40 machined into the ceramic phase, and subsequently embedded in polymer phase 34 during the lyophilization process.

In addition to altering the mechanical properties of the scaffold 30, reinforcement 38 or truss structure 70 (described below) can be utilized: (i) to modify the *in-vitro* behavior of the scaffold, 30, e.g., by introducing a different *in-vitro* profile; (ii) as a carrier for the controlled release of a drug; and (iii) as a carrier for Micro-Electro Mechanical Systems (MEMS).

Similarly, truss structures may be incorporated into the scaffold 10, 30. Figure 5 shows composite scaffold 50 having ceramic phases 52 and 54, polymer phase 60, and truss structure 70 (in phantom). Ceramic phases 52 and 54 are mechanically interlocked with polymer phase 60 at interphase regions 62 and 64 as in the embodiments described above. Figure 6 and 7 show truss structure 70, having horizontal supports 72, vertical supports 74, angular supports 76, and locking tabs 78. Truss structure 70 may be fabricated from a polymer (preferably an absorbable polymer), ceramic or composite, as listed above, by injection molding or other methods, such as stereolithography or 3-D printing, to achieve complex three-dimensional structures. The truss structure 70 provides enhanced mechanical properties for scaffold 50, i.e., in resisting compression, bending and shearing. Locking device 78 is countersunk into ceramic phases 52 and 54 to strengthen the attachment of truss structure 70 thereto. Alternatively, locking device 78 may cooperate with a mating latch element 79 affixed or formed in ceramic phases 52, 54.

Figure 8 shows an alternative truss structure 90 that can be used in a generally cylindrically shaped scaffold (not shown) otherwise having the same configuration as scaffold 50 of Figure 5. Truss structure 90 has circular supports 92, linear supports 94, and angular supports 96.

Scaffolds 10, 30, 50 may be utilized in combination with a scaffold fixation device having a post insertable into a hole bored in bone and a scaffold support disposed at 90° relative to the post. The scaffolds 10, 30, 50 can be attached to a post-type fixation device by joining the scaffold support to the ceramic phase, e.g., 32 prior to lyophilization. Alternatively, the scaffold 10, 30, 50 may be affixed in the defect region by way of calcium phosphate or calcium

sulfate cement, PMMA, fibrin glue, adhesives (such as cyanoacrylates or butyl acrylates) or simply by press fitting.

5 Solids may be added to the polymer layer e.g., 12, to promote tissue regeneration/regrowth, to act as buffers, reinforcing materials, porosity modifiers, and/or radio-opaque markers to allow imaging after implantation. Suitable solids include, but are not limited to, particles of demineralized bone, calcium phosphate particles, calcium carbonate particles for bone repair, leachable solids for pore creation and particles of bioabsorbable polymers not soluble in the solvent system as reinforcing agents or for the creation of pores as they are absorbed.

10 Suitable leachable solids include but are not limited to nontoxic leachable materials such as salts (i.e., sodium chloride, potassium chloride, calcium chloride, sodium tartrate, sodium citrate, and the like) biocompatible mono and disaccharides (i.e., glucose, fructose, dextrose, maltose, lactose and sucrose), polysaccharides (i.e., starch, alginate), water soluble proteins (i.e., gelatin and agarose) and paraffin. Generally all of these materials will have an average diameter of less than about 1 mm and preferably will have an average diameter of from about 50 to about 500  $\mu\text{m}$ . The particles will generally constitute from about 1 to about 50 volume percent of the total volume of the particle and polymer-solvent mixture (wherein the total volume percent equals 100 volume percent). The leachable materials can be removed by immersing the foam with the leachable material in a solvent in which the particle is soluble for a sufficient amount of time to allow leaching of substantially all of the particles, but which does not dissolve or detrimentally alter the foam. The preferred extraction solvent is water, most preferably distilled-deionized water. This process is described in U.S. Patent No. 5,514,378, hereby incorporated herein by reference. Preferably the foam will be dried after the leaching process is complete at low temperature and/or vacuum dried to minimize hydrolysis of the foam unless accelerated absorption of the foam is desired.

25 Various proteins (including short chain peptides), growth agents, chemotactic agents and therapeutic agents (antibiotics, analgesics, anti-inflammatories, anti-rejection (e.g. immunosuppressants) and anticancer drugs), or ceramic particles can be added to the composite scaffold 10, 30, 50 during

processing or adsorbed onto the surface or back-filled into the scaffold 10 after fabrication. The pores of the ceramic phase 14, 32, 52, 54 and/or the polymer 12, 34, 60 may be partially or completely filled with biocompatible resorbable synthetic polymers or polymers (such as collagen or elastin) or biocompatible ceramic materials (such as hydroxyapatite) and combinations thereof (that may or may not contain materials that promote tissue growth). Suitable materials include but are not limited to autograft, allograft, or xenograft bone, bone marrow, morphogenic proteins (BMPs), epidermal growth factor (EGF), fibroblast growth factor (FGF), platelet derived growth factor (PDGF), insulin derived growth factor (IGF-I and IGF-II), transforming growth factors (TGF- $\beta$ ), vascular endothelial growth factor (VEGF), platelet rich plasma (PRP) or other osteoinductive or osteoconductive materials known in the art. The polymer fillers could also be conductive or chemotactic materials, or delivery vehicles for growth factors. Examples would be recombinant or animal derived collagen, elastin or hyaluronic acid.

Bioactive coatings or surface treatments could also be applied to the surface of the scaffold 10, 30, 50. For example, bioactive peptide sequences (RGDs) could be applied to facilitate protein adsorption and subsequent cell tissue attachment.

Therapeutic agents may also be delivered via the scaffold 10, 30, 50. The polymer and blends that are used to form the scaffold 10, 30, 50 can contain therapeutic agents. For example, polymer 12, 34, 60 would be mixed with a therapeutic agent prior to forming the composite scaffold 10, 30, 50 or loaded into the scaffold after it is formed. The variety of different therapeutic agents that can be used in conjunction with the scaffold 10, 30, 50 of the present invention is vast. In general, therapeutic agents which may be administered via the scaffold 10, 30, 50 include, without limitation: anti-infectives such as antibiotics and antiviral agents; chemotherapeutic agents (i.e. anticancer agents); anti-rejection agents; analgesics and analgesic combinations; anti-inflammatory agents; hormones such as steroids; growth factors (bone morphogenic proteins (i.e. BMPs 1-7), bone morphogenic-like proteins (i.e. GFD-5, GFD-7 and GFD-8), epidermal growth factor (EGF), fibroblast growth factor (i.e. FGF 1-9), platelet derived growth factor (PDGF), insulin like growth factor (IGF-I and IGF-II), transforming growth factors (i.e.

TGF- $\beta$  I-III), vascular endothelial growth factor (VEGF); and other naturally derived or genetically engineered proteins, polysaccharides, glycoproteins, or lipoproteins. These growth factors are described in The Cellular and Molecular Basis of Bone Formation and Repair by Vicki Rosen and R. Scott Thies, published by R.G. Landes Company hereby incorporated herein by reference.

Composite scaffolds 10, 30, 50 containing bioactive materials may be formulated by mixing one or more therapeutic agents with the polymers used to make the construct, with the solvent, or with the polymer-solvent mixture that is then foamed via lyophilization. Alternatively, a therapeutic agent may be coated on the composite scaffold 10, 30, 50 with a pharmaceutically acceptable carrier that does not dissolve the scaffold 10, 30, 50. The therapeutic agents, may be a liquid, a finely divided solid, or any other appropriate physical form. Typically, but optionally, the matrix will include one or more additives, such as diluents, carriers, excipients, stabilizers or the like. The type of polymers, e.g., 14 and drug concentration can be varied to control the release profile and the amount of drug dispensed. Upon contact with body fluids, the drug will be released. If the drug is incorporated into the foam, then the drug is released as the foam undergoes gradual degradation (mainly through hydrolysis). This can result in prolonged delivery (over, say 1 to 5,000 hours, preferably 2 to 800 hours) of effective amounts (say, 0.0001 mg/kg/hour to 10 mg/kg/hour) of the drug.

As outlined in Vacanti, U.S. Patent No. 5,770,417, cells can be harvested from a patient (before or during surgery to repair the tissue) and the cells can be processed under sterile conditions to provide a specific cell type (i.e., pluripotent cells, stem cells, marrow cells, progenitor human autologous adipose tissue (PHAAT) cells or precursor cells, such as, the mesenchymal stem cells described in Caplan, U.S. Patent No. 5,486,359). These cells, e.g., myocytes, adipocytes, fibrocytes, ectodermal cell, muscle cells, osteoblast (i.e. bone cells), chondrocyte (i.e. cartilage cells), endothelial cells, fibroblast, pancreatic cells, hepatocyte, bile duct cells, bone marrow cells, neural cells, genitourinary cells (including nephritic cells) and combinations thereof may be applied or seeded into the porous composite scaffold 10, 30, 50. Autogenous, allogeneic, xenogeneic cells may be used. The cells may be cultured ex vivo and then reimplanted. Tissue may be harvested from a patient, processed to



select certain cells and/or growth factors, such as PRP (platelet rich plasma), and then reimplanted with the scaffolds 10, 30, 50 back into the patient. The implanted cells could also contain inserted DNA encoding a protein that could stimulate the attachment, proliferation or differentiation of tissue.

Cells may be implanted into the scaffold 10, 30, 50 by placing the scaffold in a cell culture such that the cells invade the micropores and macropores. The scaffold can then be implanted into the patient. The *in vitro* seeding of cells could provide for a more rapid development and differentiation process for the tissue. It is clear that cellular differentiation and the creation of tissue specific extracellular matrix is critical for the tissue engineering of a functional implant. It is known that different cell types (stromal cells and chondrocytes) can be cultured on different structures. A gradient structure also allows for co-cultured tissue scaffolds 10, 30, 50 to be generated.

One use of the construct described herein is for the repair and regeneration of articular cartilage. Articular cartilage is an example of a naturally occurring structure composed of four different zones that include the superficial or tangential zone within the first 10-20% of the structure (this includes the articular surface), the middle zone, which is 40-60% of the middle structure, the deep zone that is adjacent to the tide mark, and a transition zone between the bone and cartilage that is composed of calcified cartilage. Subchondral bone is located adjacent to the tide mark and this transitions into cancellous bone.

As described above, the present invention permits the fabrication of a scaffold, e.g., 50 having multiple layers. Because the process described above for forming multiple layers can be executed numerous times, the resultant scaffold may have a selected number of layers, each having its own characteristics of composition, porosity, strength, etc. Accordingly, the scaffold, e.g., 50 may act as a template for multiple distinct tissue zones as are present in articular cartilage.

The surface porosity of the foam can be controlled by various methods including providing a mold therefore having a plurality of upstanding pins for piercing the surface during molding or subsequently piercing the surface by needles, laser treatment, chemical treatment, etc., resulting in surface porosity ranging from impervious to porous thereby determining fluid permeability. With regard to fabricating a scaffold, e.g., 10, for repairing articular

cartilage, the scaffold 10 may have three zones, viz., a porous polymeric phase 12 which lies adjacent to cartilage tissue, a porous ceramic phase 14 which lies adjacent to bone tissue, and an interphase region 16. The phase 12 would have an upper surface (skin) may be provided with a porosity, e.g., 75 to 150  $\mu\text{m}$  to enable the passage of cells to promote ingrowth. For articular cartilage, the polymer phase 12 and ceramic phase 14 will need to support mechanical loading and thereby protect the invading cells until they have differentiated and consolidated into tissue that is capable of sustaining load. The polymer phase 12 may have a porosity of about 80 to about 95 percent with pores that are of the order of 100  $\mu\text{m}$  (about 80  $\mu\text{m}$  to about 120  $\mu\text{m}$ ). It is expected that chondrocytes will invade this zone. The ceramic phase 14 may have larger pores (about 250 $\mu\text{m}$  to about 400  $\mu\text{m}$ ) and a porosity in the range of about 50 to about 95 percent which is structurally compatible with cancellous bone. The interphase region 16 resembles the structural transition between cartilage and bone.

Several patents have proposed systems for repairing cartilage that could be used with porous scaffolds of the present invention. For example, U.S. Patent No. 5,769,899 describes a device for repairing cartilage defects and U.S. Patent No. 5,713,374, describes securing cartilage repair devices with bone anchors (both hereby incorporated herein by reference)

The scaffold 10, 30, 50 described herein may also be used for the repair and regeneration of intervertebral discs with the scaffold 10, 30, 50 synthetically re-creating the layered structure of the spinal disc. Reinforcements, e.g., 38, 70 added to the polymeric phase 12, 60 and sandwiched between the two ceramic phases may be used to simulate the complex collagen orientation found in annulus fibrosis of the spinal disc. Such reinforcements provide additional resistance to impact, and the orientation of the reinforcement can be varied to control the mechanical properties of the construct in a manner similar to the way that collagen orientation affects those of the spinal disc.

It should be understood that the embodiments described herein are merely exemplary and that a person skilled in the art may make many variations and modifications without departing from the spirit and scope of the invention as defined in the appended claims. Accordingly, all such variations and

modifications are intended to be included within the scope of the invention as defined in the appended claims. For example, the phases, e.g., 12, 14, 32, 34, 36, 52, 60, etc. may have varying thicknesses, as well as varying composition and porosity and may be open or closed cell.

5           The following examples are illustrative of the principles and practice of this invention, although not limited thereto. Numerous additional embodiments within the scope and spirit of the invention will become apparent to those skilled in the art. In these examples certain abbreviations are used such as PCL to indicate polymerized  $\epsilon$ -caprolactone, PGA to indicate polymerized glycolide, PLA to indicate polymerized (L)lactide. Additionally, the percentages in front of the copolymer indicate the respective mole percentages of each constituent.

#### Example 1

15           This example describes the preparation of a bi-layered scaffold composed of a porous polymer phase, e.g. 12, lyophilized in the presence of a porous ceramic phase, e.g. 14.

20           A solution of the polymer to be lyophilized into a foam was first prepared. In this example, a 95/5 weight ratio of 1,4-dioxane/(35/65 PCL/PGA) was weighed out. Next, the polymer and solvent were placed into a flask, which in turn was put into a water bath and stirred at 70°C for 5 hrs. Afterwards, the solution was filtered using an extraction thimble (extra coarse porosity, type ASTM 170-220 (EC)) and stored in a flask.

25           The next step was to prepare the porous ceramic phase 14. A porous ceramic tablet (15 mm X 15 mm X 1 mm) was cut from a larger block (#97CAM03/2B, CAM Implants, by Leiden, Netherlands) using a high speed diamond cutting saw (Isomet 1000 series, blade by Beuhler) operating at speeds of 300 – 350 rpm.

30           A set of 1.0-mm x 6.3-mm x 130-mm shims was placed in a 126-mm X 136-mm aluminum mold with a lip height of 16.4 mm. The shims were placed parallel to each other, 13 – 14.5 mm apart. The ceramic tablet was placed on the shims. The contact between the ceramic tablet and the supporting

shims was minimized to overlap less than 1 mm in order to expose the maximum amount of the ceramic tablet to the polymeric solution.

The solution was then added to a level of 1.67 mm in the mold, submerging the bottom face of the ceramic tablet.

5 The mold assembly was then placed on the shelf of the lyophilizer (or freeze dryer), and the freeze dry sequence begun. A laboratory scale lyophilizer (Model Freeze Mobile G from Virtis Company (Gardiner, NY), was used. The freeze dry sequence used in this example was: 1) 20°C for 15 minutes; 2) -5°C for 120 minutes; 3) -5°C for 90 minutes under vacuum 100 mT; 10 4) 5°C for 90 minutes under vacuum 100 mT; 5) 20°C for 90 minutes under vacuum 100 mT. As the solution in the mold freeze dried, the size of the polymeric phase shrank, leaving a 1 mm thick polymer phase 12 and an interphase region 16, less than 200 microns, of polymeric foam infiltrating the porous ceramic phase (tablet) 14.

15 After the cycle was completed, the mold assembly was taken out of the freeze dryer and allowed to degas in a vacuum hood for 2 – 3 hours. The scaffold 10 was then stored under nitrogen.

In the resulting scaffold, the ceramic phase 14 was bound firmly to the polymer phase 12. Figure 9 is a scanning electron micrograph (SEM) of the cross-section of the polymer foam embedded in the porous ceramic. The SEM 20 clearly shows both the macroporous ceramic 14 and the microporous polymer 12 foam in the interphase region 16 of the composite scaffold 10.

## Example 2

25 This example describes the preparation of a bi-layered scaffold such as 30 (See Figures 3 and 4) composed of a porous polymer phase 34 lyophilized in the presence of a porous ceramic phase 32, wherein the structure also contains a biodegradable reinforcing mesh 38.

30 The polymer solution was prepared as described in Example 1. A ceramic tablet, 16.0-mm X 16.9-mm X 8.3-mm, was cut from a larger block as described in Example 1. In addition, an approximately 1-mm deep annular groove was cut into one of the 16.0-mm X 16.9-mm faces of the block using a 10.5-mm circular cutter.

5 A polydioxanone (PDS) mesh (Ethicon Inc., Somerville, NJ) was cut into strips with approximate dimensions of 11 mm X 50 mm. A strip was loosely cylindrically wound over a 9.5-mm outer diameter rod and secured in a ring configuration by a hot Aaron-ram fine tip (Aaron Medical Industries, Inc., St. Petersburg, FL) that was touched to the mesh at either end of the cylinder to weld the overlapping mesh.

10 The PDS mesh ring was placed into the groove cut in the ceramic tablet. A set of 5.0-mm x 6.3-mm x 110-mm shims was placed in a 114-mm X 114-mm aluminum mold with a lip height of 16.4 mm. The shims were placed parallel to each other, 13 - 14.5 mm apart. The prepared ceramic piece was placed on the shims with the mesh ring down.

The contact between the ceramic tablet and the supporting shims was minimized with an overlap of 1 mm or less in order to expose the maximum amount of the ceramic tablet to the underlying polymeric solution.

15 The polymer solution was then added such that the solution reached a level of 5.8 – 6.0 mm in the mold, submerging the bottom face of the ceramic tablet.

20 The mold assembly was then placed on the shelf of the lyophilizer described in Example 1, and the freeze dry sequence described in Example 1 was followed. After the cycle was completed, the mold assembly was taken out of the freeze dryer and allowed to degas in a vacuum hood for 2 – 3 hours. The scaffold was then stored under nitrogen.

25 In the resulting scaffold, the ceramic tablet was securely bound to the polymer foam. The mesh was securely fixed in the original position, providing added structural integrity to the scaffold.

### Example 3

30 This example describes the preparation of a tri-layered scaffold, e.g., like scaffold 50, but without truss 70 (See Figure 5), composed of a porous polymer phase 10 sandwiched between two porous ceramic phases 52, 54.

The polymer solution was prepared as described in Example 1. Two ceramic tablets (~12 mm X ~12 mm X ~2 mm) were cut from a larger block as described in Example 1.

5 A first ceramic tablet was placed on the bottom of an aluminum mold with a lip height of 18 mm and a diameter of 70 mm. A pair of 2.0-mm x 6.3-mm x 45-mm shims was placed on the bottom of the mold beside the ceramic tablet, parallel thereto and in close proximity. A second set of identical shims was placed over the first set of shims perpendicular thereto, ~10 mm apart and over opposed top edges of the ceramic tablet. The second ceramic tablet was placed on the second set of shims, aligned with the first ceramic tablet forming a 2-mm space between the two ceramic tablets.

10 The contact between the ceramic tablets and the supporting shims was minimized to overlap less than 1 mm in order to expose the ceramic tablets to the polymeric solution. The polymeric solution was then added to the mold to a level of ~6 mm, submerging the first tablet and contacting the bottom face of the second ceramic tablet.

15 The mold assembly was then placed on the shelf of the lyophilizer described in Example 1, and the freeze dry sequence begun. The freeze dry sequence used in this example was: 1) 20°C for 15 minutes; 2) -5°C for 120 minutes; 3) -5°C for 120 minutes under vacuum 100 mT; 4) 5°C for 120 minutes under vacuum 100 mT; 5) 20°C for 120 minutes under vacuum 100 mT.

20 After the cycle, the scaffold was cut out of the polymer using a scalpel. The tri-layer scaffold was placed in an Acetone bath to a depth of 0.5 mm for approximately 1 second to remove the polymer material on the bottom surface of the scaffold to expose the ceramic phase.

#### Example 4

25 A tri-layered scaffold having a lyophilized porous polymer phase sandwiched between two porous ceramic phases, wherein the scaffold also contains a biodegradable reinforcing truss may be fabricated in accordance with the same basic procedure outlined in Example 3. The truss used in this Example has a ring form such as that shown in Figure 3, element 38. The adjacent faces of the ceramic tablets are inscribed with a circular recess as described above in  
30 Example 2. A PDS mesh ring of diameter 11mm and 2mm thickness is prepared as in Example 2 and opposing ends thereof are inserted into the circular recesses formed in the adjacent faces of the ceramic layers that are stacked in a mold as in

Example 3. The polymer is charged in the mold, lyophilized and cleaned from the bottom surface of the scaffold as in Example 3.

09892993.062701